

Original document

## JP5302199

Patent number: JP5302199  
Publication date: 1993-11-16  
Inventor: NAGASAWA TADASHI  
Applicant: BRIDGESTONE BEKAERT STEEL CODE  
Classification:  
- international: C25D21/14; C25D3/38  
- european:  
Application number: JP19920106739 19920424  
Priority number(s): JP19920106739 19920424

[View INPADOC patent family](#)

[Report a data error here](#)

### Abstract of JP5302199

PURPOSE: To control the composition of a copper plating bath by equalizing the electrolytic current in a copper ion replenishing tank to that in a plating bath. CONSTITUTION: Copper ion and hydroxide ion are supplied from a copper ion replenishing tank 1 to a copper plating bath 2 in copper plating using an insoluble electrode. The tank 1 is separated by a thin membrane impermeable to copper ion and permselective to hydroxide ion. One compartment of the tank 1 is filled with a copper plating soln., a copper metallic electrode 7 is dipped in the compartment, and electrolysis is carried out between the positive electrode 7 and a negative counter electrode to generate copper ion from the electrode 7. In this case, the electrolytic current in the tank 1 is equalized to that in the plating bath. Consequently, the composition of the copper plating bath is controlled by replenishing a plating bath contg. copper ion.

Data supplied from the *esp@cenet* database - Worldwide